

## **PROVISIONAL PRODUCT DATA**

### **S-30**

#### **PRODUCT PROPERTIES**

##### **BASE**

Viscosity, mpa.s	27,000
Colour	Off White

##### **CURING AGENT**

Viscosity, mpa's	150
Colour	Clear

##### **BASE & CURING AGENT MIXTURE**

Cured for 7 days at 23°C	
Mix Ratio (Base:Curing Agent)	10:1 (w/w)
Hardness, Shore A	28-30
Elongation at Break, %	>800
Tear Strength, kN/m	22
Mixed Viscosity mPa.s	13,500
Relative Density	1.12
Working time of Catalysed Mixture at 23°C	60 mins
Time to achieve full cure @ 23°C	24 hrs

#### **WARRANTY INFORMATION**

**MB Fibreglass believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, but it is your responsibility to thoroughly test the product in its specific application to determine performance, efficacy and safety.**